

Extreme performance lamination packaging film


Energy lives here™



Blown film - 4-layer film formulation


Thickness: 80 µm

Exceed XP 6056
 Exceed 1012MK/MA
 ExxonMobil LDPE



Monolayer extrusion coating (50 μm) onto a 4-layer blown film (80 μm) Thickness: 130 μm

- Monolayer coating -Exceed 0019XC
- Exceed XP 6056
 Exceed 1012MK/MA
 ExxonMobil LDPE



Polymer properties	Exceed XP 6056	Exceed 1012MK/MA	Exceed 0019XC	ExxonMobil LDPE 150BW	ExxonMobil LDPE 650	Test method [*] (based on)	Unit
Melt index (190°C/2.16 kg)	0.50	1.0	19	0.75	22	ASTM D1238	g/10 min
Density	0.916	0.912	0.918	0.923	0.914	ASTM D1505	g/cm³

* For detailed product information, please consult the individual grade data sheet, available on our website: www.exxonmobilchemical.com. Values given are typical and should not be interpreted as specifications. Data generated by or on behalf of ExxonMobil Chemical.











Portfolio of performance PE polymers:

- Exceed[™] XP when eXtreme Performance matters, for step-out mechanical performance and excellent processability
- Exceed[™] for superior performance with outstanding mechanical and sealing properties combined with best-in-class optics
- Enable[™] for optimum solutions, providing excellent bubble stability with HAO properties

Creating differentiated solutions. Together.

For more information: exxonmobilchemical.com/pe Visit us at ExxonMobil pavilion FG10.1 ©2019 ExxonMobil. ExxonMobil, the ExxonMobil logo, the interlocking "X" device and other product or service names used herein are trademarks of ExxonMobil, unless indicated otherwise. This document may not be distributed, displayed, copied or altered without ExxonMobil's prior oritten authorization. To the extent ExxonMobil authorizes distributing, displaying and/or copying of this document, the user may do so only if the document is unaltered and complete, including all of its headers, footers, disclaimers and other information. You may not copy this document, to or reproduce it in whole or in part on a website. ExxonMobil does not guarantee the typica (or other) values. Any data included herein is based upon analysis of representative samples and not the actual product shipped. The information with any other product or materials. We based the information on data believed to be reliable on the date compiled, but we do not represent warrant, or otherwise guarantee, expressly or impliedly the merchantability. Ritness for a particular purpose, freedom from patent infingement, suitability accurred in super is solely reponsible for all determinations regarding any use of material or product and any process in its territories of interest. We aspressly disclaim and yot loss, damage or injury directly or indirectly suffered or ourment. This document is not an endorsement of an ren/ ExxonMobil product or processe of user and the examples of the random rendersement of an ren/ ExxonMobil product or processe of comment. This document is not an endorsement of an ren/ ExxonMobil product or processe of examples in the strate of the random rendersement of an ren/ ExxonMobil product or processe of comment. This document is not an endorsement of an ren/ ExxonMobil product or processe of comment. The document is not an endorsement of an ren/ ExxonMobil product or processe of comment. The document is not an endorsement of an render seconMobil product or processe of comment. The document is not an endorsement



Blown film line BL600P

Machine specifications:

Maximum layflat: 600 mm

Layer distribution: 4-layer spiral mandrel distributor - A/B/A/C Thickness: 80 μm

Die: 3 single-screw extruders (E30P, E25P. E25E).

- A layer 30 mm Extruder E30P
- B layer E25P
- A layer 30 mm Extruder E30P
- Clayer E25E

Monolayer extrusion coating (50 $\mu m)$ onto 4-layer blown film (80 $\mu m)$:

Layer distribution: D/A/B/A/C Twin screw extruder: ZK25E x 48D Melt pump Flat film extrusion die: BSD500 Die width: 500 mm The coated sheet is cooled on the Chill Roll – Calander CL168/250/250-600P