

# Hand-wrap stretch films with excellent mechanical performance

Energy lives here™



Exceed™, Enable™ and Vistamaxx™ performance polymers can create multilayer cast hand-wrap stretch films with excellent mechanical performance, while providing opportunities for significant raw materials savings.

ExxonMobil's industry-leading performance polymers allow film producers to fabricate tailor-made hand-wrap packaging solutions. These films offer a combination of controlled toughness, elasticity, holding force, high clarity, as well as operational flexibility.

Delivered attributes	Derived benefits & potential value
<b>Superior mechanical performance</b>	<ul style="list-style-type: none"> <li>▪ Raw material savings through downgauging opportunities for more sustainable flexible film solutions</li> <li>▪ Lower film inventory requirements</li> <li>▪ Lower logistics costs</li> </ul>
<b>Tough films at reduced thickness</b> <ul style="list-style-type: none"> <li>▪ Enhanced puncture and tear resistance</li> <li>▪ Reduced neck-in and tiger striping</li> </ul>	<ul style="list-style-type: none"> <li>▪ Increased per-unit revenue through:                             <ul style="list-style-type: none"> <li>- Reduced risk of damage in transit</li> <li>- Reduced operator fatigue</li> <li>- Less overlap needed to cover pallet</li> </ul> </li> </ul>
<b>Improved holding force</b>	<ul style="list-style-type: none"> <li>▪ More secure load transit                             <ul style="list-style-type: none"> <li>- Ability to wrap more demanding loads</li> </ul> </li> </ul>
<b>Superior cling performance</b>	<ul style="list-style-type: none"> <li>▪ Potentially lower cling layer costs</li> <li>▪ Promotes load stability</li> </ul>

### Thinner, stronger cast-stretch films

The complementary benefits of Exceed™, Enable™ and Vistamaxx™ performance polymers can create 3- and 5-layer pallet stretch films with better mechanical performance than typical polyethylene products. Enable and Exceed deliver improved tenacity and tear resistance even in thinner films. Improved tenacity provides film downgauging opportunities of up to 33%. For example, a 10 micron 5-layer film based on our polymers can deliver enhanced performance compared to a 15 micron butene linear low density polyethylene (LLDPE) film. Less neck-in during wrapping is also possible, which can result in less film being required to wrap a pallet at equal load stability.


### Better protection for safer and more secure loads

Exceed and Enable solutions offer high puncture resistance at reduced gauge, helping to ensure protection of the pallet's contents. Meanwhile, the cling performance provided by Vistamaxx helps to maintain load stability.

In 3- and 5-layer cast-stretch hand-wrap films using Enable in the core and other layers allows the balance of tenacity and toughness to be tailored to meet the needs of the application.

Figure 1:

Selected properties for an Exceed and Enable formulated film and reference film.



**Table 1: Product data for an Exceed and Enable formulation film and reference film**

	Melt index (g/10 min)	Density (g/cm <sup>3</sup> )	Exceed and Enable 5-layer coex film - 10 µm	Reference 5-layer coex film - 15 µm
Exceed 3518	3.5	0.918	●	
Enable 2010	1.0	0.920	●	
ZN-LLDPE	2.0 - 2.8	0.918	●	
Vistamaxx	-	-	●	
C4-LLDPE	2.8	0.918		●
Cling agent	-	-		●

Data from tests performed by or on behalf of ExxonMobil

Test	Test method based on
Melt Index	ASTM D 1238
Density	ASTM D 1505
Elmendorf Tear	ASTM D 1922-09
Tensile NDR	ASTM D 882
Puncture Force	CEN 14477
Dart	ASTM D 1709

©2018 ExxonMobil. ExxonMobil, the ExxonMobil logo, the interlocking "X" device and other product or service names used herein are trademarks of ExxonMobil, unless indicated otherwise. This document may not be distributed, displayed, copied or altered without ExxonMobil's prior written authorization. To the extent ExxonMobil authorizes distributing, displaying and/or copying of this document, the user may do so only if the document is unaltered and complete, including all of its headers, footers, disclaimers and other information. You may not copy this document to or reproduce it in whole or in part on a website. ExxonMobil does not guarantee the typical (or other) values. Any data included herein is based upon analysis of representative samples and not the actual product shipped. The information in this document relates only to the named product or materials when not in combination with any other product or materials. We based the information on data believed to be reliable on the date compiled, but we do not represent, warrant, or otherwise guarantee, expressly or impliedly, the merchantability, fitness for a particular purpose, freedom from patent infringement, suitability, accuracy, reliability, or completeness of this information or the products, materials or processes described. The user is solely responsible for all determinations regarding any use of material or product and any process in its territories of interest. We expressly disclaim liability for any loss, damage or injury directly or indirectly suffered or incurred as a result of or related to anyone using or relying on any of the information in this document. This document is not an endorsement of any non-ExxonMobil product or process, and we expressly disclaim any contrary implication. The terms "we," "our," "ExxonMobil Chemical" and "ExxonMobil" are each used for convenience, and may include any one or more of ExxonMobil Chemical Company, Exxon Mobil Corporation, or any affiliate either directly or indirectly stewarded.

Contact us for more information:  
[exxonmobilchemical.com](http://exxonmobilchemical.com)

X0818-074E49

**ExxonMobil**  
 Energy lives here™