

ExxonMobil™ C4LL 2018 Series Blown

(Legacy name: ExxonMobil™ LLDPE LL 1002 Series Blown)

C4 Linear Low Density Polyethylene

Product Description

ExxonMobil™ C4LL 2018 resins are ethylene 1-butene linear low density polyethylene designed for the blown film process. Films made from ExxonMobil™ C4LL 2018 resins have very good tensile and toughness properties. ExxonMobil™ C4LL 2018pw.09 resin is a granular material suitable for both compounding and film production.

General

Availability ¹	<ul style="list-style-type: none"> Latin America North America
Additive	<ul style="list-style-type: none"> ExxonMobil™ C4LL 2018pw.09: Antiblock: No; Slip: No; Processing Aid: No; Thermal Stabilizer: Yes ExxonMobil™ C4LL 2018.90: Antiblock: No; Slip: No; Processing Aid: No; Thermal Stabilizer: Yes
Applications	<ul style="list-style-type: none"> Agricultural Film Bag in Box Blown Film Cast Film Food Packaging Form Fill And Seal Packaging Freezer Film Garment Film General Packaging Industrial Packaging Institutional Can Liners Liners Mulch Film Packaging Films Produce Bags On A Roll Shoppers Trash Can Liners
Revision Date	<ul style="list-style-type: none"> 04/01/2020

Resin Properties

	Typical Value (English)	Typical Value (SI)	Test Based On
Density / Specific Gravity	0.918 g/cm ³	0.918 g/cm ³	ASTM D792
Melt Index (190°C/2.16 kg)	2.0 g/10 min	2.0 g/10 min	ASTM D1238
Peak Melting Temperature	250 °F	121 °C	ExxonMobil Method

Film Properties

	Typical Value (English)	Typical Value (SI)	Test Based On
Tensile Strength at Yield MD	1200 psi	8.5 MPa	ASTM D882
Tensile Strength at Yield TD	1400 psi	9.3 MPa	ASTM D882
Tensile Strength at Break MD	4800 psi	33 MPa	ASTM D882
Tensile Strength at Break TD	3400 psi	24 MPa	ASTM D882
Elongation at Break MD	640 %	640 %	ASTM D882
Elongation at Break TD	760 %	760 %	ASTM D882
Secant Modulus MD - 1% Secant	26000 psi	180 MPa	ASTM D882
Secant Modulus TD - 1% Secant	33000 psi	230 MPa	ASTM D882
Dart Drop Impact	< 60 g	< 60 g	ASTM D1709A
Elmendorf Tear Strength MD	100 g	100 g	ASTM D1922
Elmendorf Tear Strength TD	400 g	400 g	ASTM D1922
Puncture Force	4 lbf	19 N	ExxonMobil Method
Puncture Energy	4.5 in-lb	0.51 J	ExxonMobil Method

Optical Properties

	Typical Value (English)	Typical Value (SI)	Test Based On
Gloss (45°)	24	24	ASTM D2457
Haze	25 %	25 %	ASTM D1003

Legal Statement

Tris(nonylphenol)phosphite (TNPP) CAS# 26523-78-4 is not intentionally used by ExxonMobil in this product. Although this product is not routinely tested for its presence, based on product composition knowledge this substance is not expected to be present. However, the fact that this substance is not intentionally used by ExxonMobil in this product does not exclude that trace levels of this substance may be present as a result of the specific characteristics of the raw materials and/or of the manufacturing process.

This product is not intended for use in medical applications and should not be used in any such applications.

Contact your ExxonMobil Chemical Customer Service Representative for potential food contact application compliance (e.g. FDA, EU, HPFB).

ExxonMobil™ C4LL 2018 Series Blown C4 Linear Low Density Polyethylene

Processing Statement

Film (1.0 mil/25.4 micron) made from ExxonMobil™ C4LL 2018.90 resin on a 2.5 inch (63.5 mm) blown film line with a 2.5:1 blow-up ratio, a melt temperature of 395-415°F (202-213°C), a 60 mil (1.52 mm) die gap at a rate of 10 lbs/hr/in die circumference (1.79 kg/hr/cm).

Notes

Typical properties: these are not to be construed as specifications.

¹ Product may not be available in one or more countries in the identified Availability regions. Please contact your Sales Representative for complete Country Availability.

For additional technical, sales and order assistance: www.exxonmobilchemical.com/ContactUs

©2025 ExxonMobil. ExxonMobil, the ExxonMobil logo, the interlocking "X" device and other product or service names used herein are trademarks of ExxonMobil, unless indicated otherwise. This document may not be distributed, displayed, copied or altered without ExxonMobil's prior written authorization. To the extent ExxonMobil authorizes distributing, displaying and/or copying of this document, the user may do so only if the document is unaltered and complete, including all of its headers, footers, disclaimers and other information. You may not copy this document to or reproduce it in whole or in part on a website. ExxonMobil does not guarantee the typical (or other) values. Any data included herein is based upon analysis of representative samples and not the actual product shipped. The information in this document relates only to the named product or materials when not in combination with any other product or materials. We based the information on data believed to be reliable on the date compiled, but we do not represent, warrant, or otherwise guarantee, expressly or impliedly, the merchantability, fitness for a particular purpose, freedom from patent infringement, suitability, accuracy, reliability, or completeness of this information or the products, materials or processes described. The user is solely responsible for all determinations regarding any use of material or product and any process in its territories of interest. We expressly disclaim liability for any loss, damage or injury directly or indirectly suffered or incurred as a result of or related to anyone using or relying on any of the information in this document. This document is not an endorsement of any non-ExxonMobil product or process, and we expressly disclaim any contrary implication. The terms "we," "our," "ExxonMobil Product Solutions" and "ExxonMobil" are each used for convenience, and may include any one or more of ExxonMobil Product Solutions Company, Exxon Mobil Corporation, or any affiliate either directly or indirectly stewarded.

exxonmobilchemical.com