

ExxonMobil™ HD 6480.UV

(Legacy name: ExxonMobil™ HDPE HMA 035) High Density Polyethylene

Product Description

ExxonMobil $^{\text{TM}}$ HD 6480.UV is a UV stabilized HDPE grade, characterized by excellent dimensional stability, very high stiffness and good impact strength.

General					
Availability ¹	 Africa & Middle East 		 Asia Pacific 	 Europe 	
Additive	 Thermal Stabilizer: Y 	es	UV Stabilizer: Yes		
Applications	 Industrial Pails 		 Vegetable and Bottle Crate 	es	
Revision Date	• 01/01/2017				
Resin Properties	Typical Value	(English)	Typical Value	(SI)	Test Based On
Density	0.964	g/cm³	0.964	g/cm³	ASTM D1505
Melt Index (190°C/2.16 kg)	8.0	g/10 min	8.0	g/10 min	ASTM D1238
Thermal	Typical Value	(English)	Typical Value	(SI)	Test Based On
Heat Deflection Temperature (0.45 MPa)	150	°F	66	°C	ISO 75-2/B
Peak Melting Temperature	275	°F	135	°C	ASTM D3418
Molded Properties	Typical Value	(English)	Typical Value	(SI)	Test Based On
Tensile Stress at Yield	3900	psi	27	MPa	ISO 527-2/1A/50
Tensile Strain at Yield	9	%	9	%	ISO 527-2/1A/50
Tensile Strain at Break	> 100	%	>100	%	ISO 527-2/1A/50
Flexural Modulus	170000	psi	1200	MPa	ISO 178
Environmental Stress-Crack Resistance					ASTM D1693
122°F (50°C), 10% Igepal	4	hr	4	hr	
Impact	Typical Value	(English)	Typical Value	(SI)	Test Based On
Notched Izod Impact Strength	2.8	ft·lb/in²	6.0	kJ/m²	ISO 180/1A

Additional Information

The molded properties were measured on 4 mm (157.5 mil) thick injection molded specimen based on ISO 294-1.

Heat Deflection temperature sample preparation, injection based on ISO1872. Tested flatwise position with specimen size of $80 \text{mm} \times 10 \text{mm} \times 4 \text{mm}$

ESCR was measured on 2 mm (78.7 mil) thick compression molded plate (F50, 10 % Igepal, 50°C, 122°F)

Legal Statement

Contact your ExxonMobil Chemical Customer Service Representative for potential food contact application compliance (e.g. FDA, EU, HPFB).

This product is not intended for use in medical applications and should not be used in any such applications.

Notes

Typical properties: these are not to be construed as specifications.

¹ Product may not be available in one or more countries in the identified Availability regions. Please contact your Sales Representative for complete Country Availability.

Effective Date: 01/01/2017 ExxonMobil Page: 1 of 2

ExxonMobil™ HD 6480.UV High Density Polyethylene



For additional technical, sales and order assistance: www.exxonmobilchemical.com/ContactUs

©2025 ExxonMobil. ExxonMobil, the ExxonMobil logo, the interlocking "X" device and other product or service names used herein are trademarks of ExxonMobil, unless indicated otherwise. This document may not be distributed, displayed, copied or altered without ExxonMobil's prior written authorization. To the extent ExxonMobil authorizes distributing, displaying and/or copying of this document, the user may do so only if the document is unaltered and complete, including all of its headers, footers, disclaimers and other information. You may not copy this document to or reproduce it in whole or in part on a website. ExxonMobil does not guarantee the typical (or other) values. Any data included herein is based upon analysis of representative samples and not the actual product shipped. The information in this document relates only to the named product or materials when not in combination with any other product or materials. We based the information on data believed to be reliable on the date compiled, but we do not represent, warrant, or otherwise guarantee, expressly or impliedly, the merchantability, fitness for a particular purpose, freedom from patent infringement, suitability, accuracy, reliability, or completeness of this information or the products, materials or processes described. The user is solely responsible for all determinations regarding any use of material or product and any process in its territories of interest. We expressly disclaim liability for any loss, damage or injury directly or indirectly suffered or incurred as a result of or related to anyone using or relying on any of the information in this document. This document is not an endorsement of any non-ExxonMobil product or process, and we expressly disclaim any contrary implication. The terms "we," "our," "ExxonMobil Product Solutions" and "ExxonMobil" are each used for convenience, and may include any one or more of ExxonMobil Product Solutions Company, Exxon Mobil Corporation, or any affiliate either directly or indirectly stewarded.

exxonmobilchemical.com